

TDS OF SA 87

Poly Acryl SA 87

- IDENTIFICATION OF THE SUBSTANCE/PREPARATION AND OF THE COMPANY/UNDERTAKING

Product information

Trade name : **Poly Acryl SA 87**

Company : No:771,zereshki alley tajbakhsh street , 25 km karaj special road
,Tehran-Iran

Telephone : (+98 263) 6102231-2 , (+98 263) 6102299

Telefax : (+98 263) 6102023

Email address : info@awachimie.com

Use of the Substance : **SA 87** is a styrene acrylic emulsion developed by imported special auxiliaries and functional monomers. It is normally used for constructions. Also, this resin is suitable for Laminating adhesive,manufacturing sealing coatings, plasters,tile adhesive, roof coating,and a lot of kinds of coatings which are expected to have high resistance.

- PHYSICAL AND CHEMICAL PROPERTIES

Physical state	liquid
Colour	milky
Odour	faint
Total solid (ASTM D 2369)	50±1%
Viscosity (23°C, Brookfield RV #5/RPM 10)	180-400 P
pH (ASTM D 1293)	7.5-9
MFFT (ISO 2811)	<0°C
Density (ASTM D1475)	1/04±0.02g/cm ³
Water solubility	dilutable

- FIRST AID MEASURES

General advice

Remove contaminated or saturated clothing.

Skin contact

Wash off with plenty of water and soap immediately.

Eye contact

Rinse with plenty of water immediately, seek medical advice if necessary.

Ingestion.

Seek medical advice.

- HANDLING AND STORAGE**Handling****Safe handling advice**

Avoid contact with skin and eyes.

Application, processing: Provide good ventilation or extraction.

Advice on protection against fire and explosion

Normal measures for preventive fire protection.

Storage**Requirements for storage areas and containers**

Keep container tightly closed.

Protect from frost.

- OTHER INFORMATION

NOTICE: Awa shimi believes the information contained here is accurate. However, Awa shimi makes no warranty, expressed or implied, regarding the accuracy of this data or the results to be obtained by the use thereof. , Awa shimi assumes no responsibility for injury from the use of the product described herein.